



PALBOND

Aluminum Composite Panel



► Introduction

PALBOND is an advanced multilayered composite panel with special features for advertising applications. A special colored coating on one side provides a soft and attractive appearance, while PALBOND's robust structure offers extreme toughness and weather resistance for outdoor applications.

► Standard Colors*

Property	Standard
Traffic Yellow	1023
Traffic Red	3020
Traffic Blue	5017
Traffic Green	6024
Jet black	9005
Traffic White (Grey coating on back side)	9016
Grey	9006
Silver	-

*Other colors are available, subject to minimum quantity.
For more information please contact your PALRAM distributor.

► Main Benefits

- Extremely durable - No cracking or breaking
- Easily formed - No heating required
- High resistance to chemicals and solvents
- Weather resistant - For external uses
- Smooth and uniform - Visually attractive
- Easily bent, curved, drilled, routed, punched and shaped
- Lightweight

► Typical Applications

- Attractive advertising signage
- Traffic signage
- Anti-vandal signage
- Large printed images
- Three dimensional signage



► Typical Physical Properties

	Property	Method	Value
PANEL	Weight	ASTM D-792	4.5 Kg/m ²
	Service temperature		-50°C to +80°C
	Thermal expansion	ASTM D-696	24 - 28
	Flexural rigidity	ASTM C-393	14x10 ⁵ Kg/mm ²
	Impact resistance	ASTM D-732	1.650 Kgf
	Adhesive strength	ASTM D-903	0.78 Kg/mm
	Flexural elasticity	ASTM D-790	4055 Kg/mm ²
	Minimum bending radius	ASTM D-696	45 mm
	Wind pressure resistance	ASTM E-84	Passed
	Water tightness	ASTM D-331	Passed
COATING	Thickness	ISO-2360 (CNS84)	4.5 Kg/m ²
	Gloss	ASTM D532-89	5-80 Kg/m ²
	Pencil hardness	ASTM D-3363-74	2H
	Toughness	ASTM D-4145-83	2T, no rift
	Adhesive force	ASTM D-3359-87	100/100 - no peel
	Impact resistance	ASTM D-2794	No crack
	Abrasion resistance	ASTM D-968-81	50-80 KTR - No crack
	Mortar resistance	ASTM D-605.2-90	24Hr - PAT test exceed
	Humidity resistance	ASTM E-714-87	300Hr - No blister
	Boiling water resistance	ASTM D-3359-B	Passed
	Salt spray resistance	ASTM D-117-94	300Hr - No blister
	Acid resistance	ASTM D-1308-87	No effect
	Alkali resistance	ASTM D-1308-87	Passed
	Solvent resistance	ASTM D-2248-73	Passed
	Color retention	ASTM D-2248-73	E<5
Chalk resistance	ASTM D-4214-89	Max value: 8 units	
Gloss retention	ASTM D-903	0.78 Kg/mm	

► Flammability

PALBOND's fire resistance exceeds Class B1 of the DIN 4102 flammability test. PALBOND also performs excellent in flame spread and smoke development tests.

Standard	Classification*
ASTM E-84-04	Up to 1550
BS 476:Part 6&7	Class 0
DIN 4102-1	B1

Inasmuch as PALRAM Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any PALRAM Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. PALRAM Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local PALRAM Industries supplier to ensure that you have obtained the most up to date information.

Europe
UK
Israel
USA
Australia
Far East



EUROPE
PALRAM EUROPE LTD.
Tel: +44-1302-380776
Fax: +44-1302-380788
sales.europe@palram.com
www.palram.com

PALRAM UK
Tel: +44-1302-380738
Fax: +44-1302-380788
sales.uk@palram.com

ISRAEL
PALRAM ISRAEL
Tel: +972-4-8459900
Fax: +972-4-8459980
palram@palram.com
www.palram.co.il

USA
PALRAM AMERICAS
Tel: +610-2859918
Fax: +610-2859928
palramamericas@palram.com
www.palramamericas.com

©2008 PALRAM Industries Ltd.
PALBOND is a trademark of PALRAM Industries Ltd.

► Product Options

Property	Standard	Special Options*
Total Thickness	3mm	2, 3, 4, 5, 6mm
Aluminum Foil Thickness	30µm	27µm
Coating	Polyester - One side	PVDF/Polyester - Both sides
Length	2440mm	Up to 6000mm
Width	1220	Up to 1550
Warranty	8 years	10 years (PVDF)
Colors	Standard (See front)	Over 30 available
Fire Retardant (FR)	-	Upon special request

*Other dimensions are available, subject to minimum quantity.
For more information please contact your PALRAM distributor.

► Fabrication

PALBOND offers numerous fabrication options while maintaining its toughness and durability.

